

PRODUCT SPECIFICATION SHEET

Product Name: 3M™ Fire Barrier Pillows

Typical Physical Properties

Blanket Color: 3M Red

Density: 6 PCF (nominal)

Performance

3M Fire Barrier Pillow has been tested in accordance with ASTM E 84

Specifications	
Density:	6 PCF (nominal)
Heat Expansion Begins:	392°F (200°C)
Significant Expansion Begins:	536°F (280°C)
Volume Expansion:	18% (calculated)

L Rating: See UL Listing.

Installation shall be in strict accordance with manufacturer's written instructions. The product shall be classified by Underwriter's Laboratory, Inc. as a Fill, Void and Cavity Material. When installed in accordance with systems outlined in the current UL Fire Resistance Directory and tested in accordance with ASTM E 814 and (UL 1479), up to a 3 hour rating is achieved.