



ANTI-SLIP SOLUTIONS
mail@heskins.com

www.heskins.com

01/10/2015

UV ageing/resistance test

Material description:	Coarse safety-grip
Colour:	Black
Test equipment:	Accelerated weathering tester, model QUV/SE
Ambient temperature:	25°C $\pm$ 3°C
Relative humidity:	55 $\pm$ 20% RH
Test method:	ASTM G154-06 cycle I, standard practice for operating fluorescent light apparatus for UV exposure of non-metallic material
Lamp:	UVA340nm
Typical irradiance:	0.89W/m ² /nm
Exposure cycle:	UV60°C/8hrs; condensation 50°C/4hrs
Time:	24hrs
Test result:	No variation

All the above data is for reference only.
©Heskins Ltd 1997-2009